



A NuWave Solutions Company

---

## ASTM D335, ASTM B117 SPECIFICATIONS

**Coating Adhesion Test Data for Galv-Match-Plus™** - (65% zinc-rich coating) per ASTM-D335 Test Method B

Substrate: Cold-Rolled Steel and Galvanized Steel Rating: 5B "NO TAPE OFF"

**Coating Adhesion Test Data for Prime-Zinc-Plus™** - (95% zinc-rich coating) per ASTM-D3359 Test Method B

Substrate: Cold-Rolled Steel and Galvanized Steel Rating: 5B "NO TAPE OFF"

**Salt-Spray Corrosion Test Data for Galv-Match-Plus™** (65% zinc-rich coating) Per ASTM B117

Substrate: Untreated Cold Rolled Steel, Duration: 500 Hours.

**ASTM D714:** Medium #8 Blister with Red Rust

**ASTM D1654:** Un-scribed Area Rating#6\*, Scribed Area Rating #9\*, Substrate: Hot Dip Galvanizing Steel Duration: 1,000 hours

**ASTM D714:** Medium #6 Blisters no red rust

**ASTM D1654:** Un-scribed Area Rating #10\*, Scribed Area Rating #10\*

**Salt-Spray Corrosion Test for Prime-Zinc-Plus™** - (95% zinc-rich coating) Per ASTM B117, Substrate: Untreated Cold Rolled Steel, duration: 500 Hours

**ASTM D714:** Medium #8 Blister, No Red Rust

**ASTM D1654:** Un-scribed Area Rating#8\*, Scribed Area Rating #9\*, Substrate: Hot Dip Galvanizing Steel Duration: 500 hours

**ASTM D714:** Few #4 Blisters, Slight White Rust

**ASTM D1654:** Un-scribed Area Rating #6\*, Scribed Area Rating #10\*,

\* Rate Scale: 0 = Worst, 10 = Best